

Iten Industries

Commercial Vulcanized Fibre Performance Values

<u>Properties</u>	<u>Test Condition</u>	<u>ASTM</u>	<u>Values</u>
Thickness			.125 inches
Tensile Strength:	Lengthwise	D638	15,400 psi
	Crosswise		8,600 psi
Flexural Strength:	Condition A Lengthwise	D790	20,000 psi
	Condition A Crosswise		13,400 psi
Compressive Strength:	Lengthwise	D695	8,900 psi
	Crosswise		7,700 psi
Izod Impact (notched):	Condition A Lengthwise	D256	4.23 ft.lb./in.
	Condition A Crosswise		3.53 ft.lb./in.
	D48/50 Lengthwise		8.63 ft.lb./in.
	D48/50 Crosswise	D256	6.61 ft.lb./in.
	E48/50 Lengthwise		2.28 ft.lb./in.
	E48/50 Crosswise		1.81 ft.lb./in.
Water Absorption		D570	35.43% of weight
Specific Gravity		D792	1.39
U.L. Subject 94		UL94	94HB
Dielectric Strength		D149	139 Vpm
Dielectric Breakdown:	Condition A	D149	66 Kv
	D48/50		1.5 Kv
Arc Resistance:	Condition A	D495	116 seconds
	D48/50		0 seconds
Permittivity, 1MHz:	Condition A	D150	6.39
	D24/23		21.02
Dissipation Factor, 1MHz:	Condition A	D150	0.0581
	D24/23		0.5506
Permittivity, 1KHz:	Condition A	D150	7.98
Dissipation Factor, 1KHz:	Condition A	D150	0.1329
	D24/23		4.6669
U.L. temperature Index:	Electrical		90° C
	Mechanical		90° C

Ashtabula, Ohio 44004 440-997-6134 Fax 440-992-3614
and
Addison, Illinois 60101 630-543-2880 Fax 630-543-1463

All values are average test results from typical production material. No warranty is implied or guaranteed and testing is recommended for each application.

Imagineering With Plastics

Nov. 10, 1997

The above test results are an average result of purchased commercial vulcanized fibre from NVF