

Iten Industries

Politen® ESP185 Performance Values

<u>Properties</u>	<u>Test Condition</u>	<u>ASTM</u>	<u>Values</u>
Thickness			.125 inches
Tensile Strength:	Lengthwise	D638	10,300 psi
	Crosswise		9,600 psi
Flexural Strength:	Condition A Lengthwise	D790	19,100 psi
	Condition A Crosswise		17,400 psi
	D48/50 Lengthwise		18,300 psi
	D48/50 Crosswise		15,400 psi
Compressive Strength:	Lengthwise	D695	18,200 psi
	Crosswise		16,200 psi
Izod Impact (notched):	Condition A Lengthwise	D256	9.6 ft.lb./in.
	Condition A Crosswise		7.7 ft.lb./in.
	D48/50 Lengthwise		10.2 ft.lb./in.
	D48/50 Crosswise		9.7 ft.lb./in.
	E48/50 Lengthwise		10.7 ft.lb./in.
	E48/50 Crosswise		10.0 ft.lb./in.
Water Absorption		D570	.25% of weight
Specific Gravity		D792	1.67
U.L. Subject 94		UL94	94 HB
Dielectric Strength		D149	216 Vpm
Dielectric Breakdown:	Condition A	D149	54.0 kV
	D48/50		26.0 kV
Arc Resistance:	Condition A	D495	114 seconds
	D48/50		125 seconds
Permittivity, 1MHz:	Condition A	D150	4.65
	D24/23		4.69
Dissipation Factor, 1MHz:	Condition A	D150	0.0120
	D24/23		0.0150
Permittivity, 1KHz:	Condition A	D150	4.91
	D24/23		5.14
Dissipation Factor, 1KHz:	Condition A	D150	0.0130
	D24/23		0.0370
Permittivity, 60Hz:	Condition A	D150	4.71
	D24/23		5.55
Dissipation Factor, 60Hz:	Condition A	D150	0.0120
	D24/23		0.1740
Temperature Rating:	Electrical		185° C
	Mechanical		185° C
Thermal Conductivity *		2.0 Btu-in/hour- square foot-°F	
Coefficient of Thermal Expansion *		.7 in/in/°C-10 ⁻⁵ .	
Halogen Content			0%

* Nominal values

ESP185 was formerly HT2

Standard Sheet sizes are 36" x 72", 48" x 72", & 49" x 97"

Ashtabula, Ohio 44004 440-997-6134 Fax 440-992-3614

Addison, Illinois 60101 630-543-2820 Fax 630-543-1463

All values are average test results from typical production material. No warranty is implied or guaranteed and testing is recommended for each application.

itenindustries.com

Imagineering with Plastics

May 30, 2001