

Iten Industries

Politen® G2FR05 (GPO2) Performance Values

<u>Properties</u>	<u>Test Condition</u>	<u>ASTM</u>	<u>Values</u>	
Thickness			.125 inches	
Tensile Strength:		Lengthwise	D638	12,900 psi
		Crosswise		9,300 psi
Flexural Strength:	Condition A	Lengthwise	D790	26,800 psi
	Condition A	Crosswise		22,200 psi
	D48/50	Lengthwise		26,800 psi
	D48/50	Crosswise		22,100 psi
Compressive Strength:		Lengthwise	D695	30,600 psi
		Crosswise		24,800 psi
Izod Impact (notched):	Condition A	Lengthwise	D256	8.6 ft.lb./in.
	Condition A	Crosswise		8.6 ft.lb./in.
	D48/50	Lengthwise		8.1 ft.lb./in.
	D48/50	Crosswise	D256	7.5 ft.lb./in.
	E48/50	Lengthwise		9.3 ft.lb./in.
	E48/50	Crosswise		8.3 ft.lb./in.
Water Absorption			D570	.12% of weight
Specific Gravity			D792	1.81
U.L. Subject 94			UL94	V-0
Dielectric Strength			D149	333 Vpm
Dielectric Breakdown:	Condition A		D149	89.6 kV
	D48/50			40.0 kV
Arc Resistance:	Condition A		D495	146 seconds
	D48/50			137 seconds
Permittivity, 1MHz:	Condition A		D150	4.00
	D24/23			3.97
Dissipation Factor, 1MHz:	Condition A		D150	0.0145
	D24/23			0.0162
Permittivity, 1KHz:	Condition A		D150	4.19
	D24/23			4.32
Dissipation Factor, 1KHz:	Condition A		D150	0.0127
	D24/23			0.0213
U.L. temperature Index:		Electrical		130° C
		Mechanical		160° C

G2FR05 (formerly GE3FR) meets NEMA specifications for GPO 2

Standard Sheet sizes are 36" x 48", 48" x 48", 48" x 72", & 48" x 96"

Ashtabula, Ohio 44004 440-997-6134 Fax 440-992-3614

Addison, Illinois 60101 630-543-2820 Fax 630-543-1463

All values are average test results from typical production material. No warranty is implied or guaranteed and testing is recommended for each application.

www.itenindustries.com

Imagineering with Plastics

August 16, 2001