

Iten Industries

Politen® G3TR10 (GPO3) Performance Values

<u>Properties</u>	<u>Test Condition</u>	<u>ASTM</u>	<u>Values</u>
Thickness			.125 inches
Tensile Strength:	Lengthwise	D638	12,000 psi
	Crosswise		8,300 psi
Flexural Strength:	Condition A Lengthwise	D790	25,700 psi
	Condition A Crosswise		17,600 psi
	D48/50 Lengthwise		24,300 psi
	D48/50 Crosswise		19,000 psi
Compressive Strength:	Lengthwise	D695	30,300 psi
	Crosswise		27,300 psi
Izod Impact (notched):	Condition A Lengthwise	D256	6.7 ft.lb./in.
	Condition A Crosswise		6.3 ft.lb./in.
	D48/50 Lengthwise		6.3 ft.lb./in.
	D48/50 Crosswise		6.0 ft.lb./in.
	E48/50 Lengthwise		7.1 ft.lb./in.
	E48/50 Crosswise		6.7 ft.lb./in.
Water Absorption		D570	.27% of weight
Specific Gravity		D792	1.76
U.L. Subject 94		UL94	V-0
Dielectric Strength		D149	307 Vpm
Dielectric Breakdown:	Condition A	D149	82.5 kV
	D48/50		39.0 kV
Arc Resistance:	Condition A	D495	156 seconds
	D48/50		137 seconds
Comparative Track Index (CTI)		U.L. 746A	500 Volts
U.L HV Track Rate		U.L. 746A	0 mm/Min.
Permittivity, 1MHz:	Condition A	D150	3.98
	D24/23		4.09
Dissipation Factor, 1MHz:	Condition A	D150	0.0130
	D24/23		0.0171
Permittivity, 1KHz:	Condition A	D150	4.17
	D24/23		4.38
Dissipation Factor, 1KHz:	Condition A	D150	0.0108
	D24/23		0.0186
U.L. Hot Wire Ignition		U.L. 746A	258 seconds
U.L. High Amp Ignition		U.L. 746A	200 + Exposure
U.L. temperature Index:	Electrical		105° C
	Mechanical		140° C

G3TR10 was formerly G2FR

Standard Sheet sizes are 36" x 72", 48" x 72", & 49" x 97"
 Ashtabula, Ohio 44004 440-997-6134 Fax 440-992-3614
 and
 Addison, Illinois 60101 630-543-2820 Fax 630-543-1463

All values are average test results from typical production material. No warranty is implied or guaranteed and testing is recommended for each application.

www.itenindustries.com

Imagineering with Plastics

July 19, 2000

