

Iten Industries

Resiten® LFBI Performance Values

A fine weave cotton fabric/phenolic laminate that meets or exceeds NEMA grade L

<u>Properties</u>	<u>Test Condition</u>	<u>ASTM</u>	<u>Values</u>	<u>Values</u>	<u>Values</u>
Thickness			.062 inches	.125 inches	.500 inches
Tensile Strength:	Lengthwise	D638	9,130 psi	11,000 psi	
	Crosswise		9,040 psi	9,300 psi	
Flexural Strength:	Condition A Lengthwise	D790	16,400 psi	16,800 psi	18,000 psi
	Condition A Crosswise		19,900 psi	16,500 psi	14,800 psi
	D48/50 Lengthwise		18,200 psi	17,300 psi	
	D48/50 Crosswise		18,200 psi	17,000 psi	
Compressive Strength:	Lengthwise	D695	7,170 psi	20,900 psi	27,900 psi
	Crosswise		5,870 psi	18,900 psi	27,400 psi
	Flatwise			> 45,000 psi	> 45,000 psi
Izod Impact (notched):	Condition A Lengthwise	D256	1.26 ft.lb./in.	1.2 ft.lb./in.	1.78 ft.lb./in.
	Condition A Crosswise		1.18 ft.lb./in.	1.11 ft.lb./in.	1.00 ft.lb./in.
	D48/50 Lengthwise		1.37 ft.lb./in.	1.5 ft.lb./in.	1.24 ft.lb./in.
	D48/50 Crosswise		1.07 ft.lb./in.	1.14 ft.lb./in.	1.09 ft.lb./in.
	E48/50 Lengthwise		1.13 ft.lb./in.	1.21 ft.lb./in.	1.11 ft.lb./in.
	E48/50 Crosswise		1.11 ft.lb./in.	1.19 ft.lb./in.	.99 ft.lb./in.
Bond Strength	Condition A	D229			1,620 pounds
	D48/50				1,870 pounds
Water Absorption		D570	1.56% of weight	1.05% of weight	.79% of weight
Specific Gravity		D792	1.33	1.33	1.32
U.L. Subject 94		UL94	HB	HB	V-O
Dielectric Strength		D149	485 Vpm	270 Vpm	
Dielectric Breakdown:	Condition A	D149	41 kV	35 kV	15 kV
	D48/50		4 kV	5 kV	8 kV
Arc Resistance:	Condition A	D495	39 seconds	54 seconds	45 seconds
	D48/50		6 seconds	7 seconds	50 seconds
Permittivity, 1MHz:	Condition A	D150	4.83	5.06	
	D24/23		5.22	5.32	
Dissipation Factor, 1MHz:	Condition A	D150	.050	.056	
	D24/23		.064	.066	
Permittivity, 1KHz:	Condition A	D150	6.75	7.54	
	D24/23		8.41	9.03	
Dissipation Factor, 1KHz:	Condition A	D150	.154	.198	
	D24/23		.228	.260	
U.L. temperature Index:	Electrical		115° C	115° C	115° C
	Mechanical		125° C	125° C	125° C

Resiten® is a halogen free laminate

Resiten® LFBI meets NEMA specifications for L, Mil type FBI, & GE A19B16A1 & A2

Standard Sheet sizes are 36" x 48" & 48" x 48"

Ashtabula, Ohio 44004 440-997-6134 Fax 440-992-3614

Addison, Illinois 60101 630-543-2820 Fax 630-543-1463

All values are average test results from typical production material. No warranty is implied or guaranteed and testing is recommended for each application.

www.itenindustries.com

Imagineering with Plastics

May 14, 2001